

GoatThroat™ Chemical Compatibility Guide

		GT 100	GT 200	GT 200S	GT 300
A		NITRILE	EPDM	Santoprene	VITON
	2,4-D Amine 500	Do Not Use	Good	[n/r]	[n/r]
	2,4-D Ester 800	[n/r]	[n/r]	[n/r]	Best
	ACB - 30	Best	Best	[n/r]	[n/r]
Wash	Acetaldehyde	Do Not Use	Best	[n/r]	Caution
	Acetamide	Best	Best	[n/r]	Best
	Acetic Acid 10%	Do Not Use	Good	Best	Caution
	Acetic Acid up to 25%	Best	Best	Best	Best
	acetic acid up 25 - 85%	Good	Best	Best	Best
	acetic acid 56%	good	good	best	good
	acetic acid, glacial, technically pure	Do Not Use	nd	Best	good
Wash	Acetic Anhydride	Do Not Use	Caution	best	Do Not Use
Test	Acetone	Do Not Use	Caution	Best	Do Not Use
	Acetone, tehcnically pure	caution	Best	best	Good
	Acetone, Trces	Good	Best	best	Good
	Acetophenone	Do Not Use	Best	[n/r]	Caution
	Acetyl Acetone	Caution	Best	[n/r]	Caution
Test	Acetylene	Best	Caution	Best	Best
	Acetylene Tetrabromide	[n/r]	Best	[n/r]	Best
Test	Acrylonitrile (Vinyl Cyanide)	Do Not Use	Best	[n/r]	Do Not Use
	Acrylonitrile (Vinyl Cyanide)	Do Not Use	Best	best	Do Not Use
	ACTICIDE 14	[n/r]	[n/r]	[n/r]	Best
	ACTICIDE A2	[n/r]	[n/r]	[n/r]	Best
	ACTRIL DS	[n/r]	[n/r]	[n/r]	Best
	Aircraft Soap	best	best	best	best
	AGRITOX	Best	[n/r]	[n/r]	[n/r]
	ALBAROL	[n/r]	[n/r]	[n/r]	Best
Wash	Alkazene	Caution	Caution	[n/r]	Good
	Allyl Alcohol	Best	Do Not Use	Do Not Use	Caution
	Alpha Cypermethryn	[n/r]	[n/r]	[n/r]	Best
	Aluminium Acetate	Best	Best	[n/r]	Best
	Aluminium Bromide	Best	Best	[n/r]	Best
	Aluminium Chloride 20%	Best	Best	Best	Best
	Aluminium Fluoride 20%	Best	Best	[n/r]	Best
	Aluminium Nitrate	Best	Best	[n/r]	Best
	Aluminium Salts	Best	[n/r]	[n/r]	[n/r]
	Aluminium Sulfate 10%	Best	Best	Best	Best
	Alums- NH3-Cr-K	Best	Best	best	Caution
	Ammonium Carbonate 10%	Best	Best	best	Best
Test	Ammonium Chloride	Good	Best	Best	Best
	Ammonium Dibasic	Best	[n/r]	[n/r]	[n/r]
	Ammonium Hydroxide	Good	Best	Best	Good
	Ammonium Monobasic	Best	[n/r]	[n/r]	[n/r]
	Ammonium Nitrate	Best	Best	best	Best
	Ammonium Persulfate	Do Not Use	Best	[n/r]	Best
	Ammonium Phosphate(Di, Tri, & Mono)	Best	Best	best	Best
	Ammonium Salts	Best	[n/r]	[n/r]	[n/r]
	Ammonium Sulfate	Best	Best	best	Best
	Ammonium Sulphide	Best	Best	[n/r]	Best
Wash	Amyl- Acetate	Do Not Use	Good	Best	Do Not Use
	Amyl- Alcohol	Good	Best	Best	Best
	Amyl- Borate	Best	Good	[n/r]	Best
	Amyl- Chloride	Good	Do Not Use	[n/r]	Good
	Amyl Naphthalene	Do Not Use	Caution	[n/r]	Best
	Anhydrous Ammonia	[n/r]	Best	[n/r]	[n/r]
	Anhydrous Hydrazine	[n/r]	Best	[n/r]	[n/r]
	Anhydrous Hydrogen Fluoride	[n/r]	Best	[n/r]	[n/r]
	Aniline	Do Not Use	Good	Best	Good
	Aniline Dyes	Caution	Caution	[n/r]	Good
	Aniline Hydrochloride 20%	Good	Good	[n/r]	Best
	Aniline Oil	Do Not Use	Good	[n/r]	Best
	Animal Fats	Best	Best	[n/r]	Best
	Anti Freeze (glycol)	best	good	good	do not use
	Aqua Regia	Do Not Use	Good	[n/r]	Caution
	Arsenic Acid	Best	Best	best	Best

		GT 100	GT 200	GT 200S	GT 300
B		NITRILE	EPDM	Santoprene	VITON
	ASE-60	Best	[n/r]	[n/r]	[n/r]
	Automatic Transmission Fluid	Best	Caution	[n/r]	Best
	Automotive Brake Fluid	Caution	Best	[n/r]	Caution
	Baking Soda	Best	[n/r]	Best	[n/r]
	Barium Chloride	Best	Best	[n/r]	Best
	Barium Hydroxide	Best	Best	Best	Best
	Barium Salts	Best	[n/r]	[n/r]	[n/r]
	Barium Sulfide	Good	Best	[n/r]	Best
	BARREL	[n/r]	[n/r]	[n/r]	Best
	BAYCOR 300	[n/r]	Best	[n/r]	[n/r]
	BAYFIDAN 250 EC	[n/r]	Best	[n/r]	[n/r]
Test	BAYLETON 125 EC	[n/r]	[n/r]	[n/r]	Best
Test	BAYTAN C Flowable seed dressing	Best	[n/r]	[n/r]	[n/r]
	Beer	Good	Best	Best	Best
Test	Beet Sugar Liquors	Best	Best	[n/r]	Best
	Benzaldehyde 10%	Do Not Use	Caution	[n/r]	Caution
	Benzene	Do Not Use	Do Not Use	Do Not Use	Good
	Benzenesulfonic Acid 10%	Do Not Use	Caution	[n/r]	Best
	Benzine	Do Not Use	Good	[n/r]	Do Not Use
Test	Benzochloride	[n/r]	Best	[n/r]	[n/r]
	Benzoic Acid	Good	Caution	Best	Best
	Benzyl Alcohol	Do Not Use	Good	[n/r]	Best
	Benzyl Benzoate	Do Not Use	Good	[n/r]	Best
	Benzyl Chloride	Do Not Use	Do Not Use	[n/r]	Best
	Black Sulphate Liquors	Best	Best	[n/r]	Best
	BLAZER	Best	[n/r]	[n/r]	[n/r]
	Borax (Sodium Borate)	Good	Best	Best	Best
	Bordeaux Mixture (Copper Sulfate Salt)	Best	Best	[n/r]	Best
	Boric Acid	Best	Best	Best	Best
	Boron Fluids	Best	[n/r]	[n/r]	Best
Test	Brake Fluid (non petroleum)	Do Not Use	Best	[n/r]	Caution
Test	Brine	Best	Best	[n/r]	Best
	BRODAL	Best	[n/r]	[n/r]	[n/r]
	Bromine	Caution	Good	[n/r]	Best
	Bromine- Water	Do Not Use	Do Not Use	[n/r]	Best
	Bromobenzene	Do Not Use	Do Not Use	[n/r]	Best
	Bromochloro Trifluoroethane	[n/r]	[n/r]	[n/r]	Best
	Bruiln 850	do not use	do not use	do not use	best
	BRYTOFA	Best	[n/r]	[n/r]	[n/r]
	BUCTRIL MA	[n/r]	[n/r]	[n/r]	Best
	BUCTRIL 200	[n/r]	[n/r]	[n/r]	Best
	BUGMASTER FLO	Best	[n/r]	[n/r]	[n/r]
Test	BULLDOCK 25 EC	[n/r]	[n/r]	[n/r]	Best
	BULLDOCK 8 UL	[n/r]	[n/r]	[n/r]	Best
	Bunker Oil	Best	Do Not Use	[n/r]	Best
	Butadiene	Good	Do Not Use	Do Not Use	Best
	Butane (LPG)	Best	Good	Best	Do Not Use
	Butane (LPG)	Best	Do Not Use	Do Not Use	Best
	Butanol	Good	Best	good	Good
	Butter	Best	Best	[n/r]	Best
	Butyl Acetyl Rincinoleate	[n/r]	Caution	[n/r]	Best
	Butyl Acetate	Do Not Use	Best	Best	Do Not Use
	Butyl Alcohol	Good	Best	[n/r]	Good
	Butyl Amine	Best	Do Not Use	[n/r]	Best
	Butyl Carbitol	Best	Best	[n/r]	Best
	Butyl Cellosolve	Do Not Use	Best	[n/r]	Do Not Use
Test/Wash	Butyl Cellosolve Adipate	Caution	Best	[n/r]	Caution
Wash	Butyl Oleate	Good	Caution	[n/r]	Best
	Butyl Stearate	Good	Caution	[n/r]	Best
	Butylene	Best	Do Not Use	Do Not Use	Best
	Butyralderhyde	Caution	Caution	[n/r]	Caution
	Butyric Acid	Do Not Use	Best	Best	Best

GoatThroat™ Chemical Compatibility Guide

		GT 100	GT 200	GT 200S	GT 300
D		NITRILE	EPDM	Santoprene	VITON
Wash	Diocetyl Phthalate	Good	Best	Good	Best
Wash	Diocetyl Sebacate	Do Not Use	Caution	[n/r]	Caution
	Dipentene	Good	Caution	[n/r]	Best
	Diphenyl	Do Not Use	Do Not Use	[n/r]	Best
Test	Diphenyl Oxide	Do Not Use	Do Not Use	[n/r]	Best
	DIPTEREX 500 SL	[n/r]	Best	[n/r]	[n/r]
	Distilled Water	Best	Best	Best	Best
	DIURON FLOWABLE	Best	[n/r]	[n/r]	[n/r]
	DODINE FLOWABLE	Best	[n/r]	[n/r]	[n/r]
	DOT Brake Fluid	best	best	best	best
*	Dry Cleaning Fluid	best	good	best	good
*	Dry Cleaning Fluids	Caution	Caution	[n/r]	Best
	DTE Light oil	Best	[n/r]	[n/r]	[n/r]

E					
	ENDOSULFAN	[n/r]	[n/r]	[n/r]	Best
	ENDOSULFAN ULV	[n/r]	[n/r]	[n/r]	Best
	Engine Oil	best	good	good	do not use
	Epoxy Resins	[n/r]	Best	[n/r]	[n/r]
	ESI-CRYL 11	Best	[n/r]	[n/r]	[n/r]
	Ethane	Best	Do Not Use	[n/r]	Best
	Ethanol	Best	Best	Best	Best
	Ethanol 95%	Best	Best	Good	Best
Test	Ethanolamine	Best	Best	[n/r]	Do Not Use
Wash	ETHREL	Good	[n/r]	[n/r]	[n/r]
Wash	Ethyl Acetate	Do Not Use	Good	Best	Do Not Use
Wash	Ethyl Acetoacetate	Do Not Use	Best	[n/r]	Do Not Use
Wash	Ethyl Acrylate	Do Not Use	Good	[n/r]	Do Not Use
	Ethyl Alcohol	[n/r]	Best	Best	Best
Test	Ethyl Benzene	Caution	Do Not Use	Do Not Use	Best
	Ethyl Benzoate	Caution	Caution	[n/r]	Best
	Ethyl Bromide	[n/r]	[n/r]	[n/r]	Best
	Ethyl Cellosolve	Good	Good	[n/r]	Do Not Use
Wash	Ethyl Cellulose	Good	Good	[n/r]	Best
	Ethyl Chloride	Good	Best	Good	Best
	Ethyl Chlorocarbonate	[n/r]	[n/r]	[n/r]	Best
Test/Wash	Ethyl Chloroformate	Do Not Use	Good	[n/r]	Do Not Use
	Ethyl Formate	Do Not Use	Caution	[n/r]	Best
	Ethyl Oxalate	Do Not Use	Best	[n/r]	Do Not Use
Test	Ethyl Pentochlorobenzene	Caution	Caution	[n/r]	Best
	Ethyl Silicate	Best	Best	[n/r]	Best
Wash	Ethylacrylic Acid	[n/r]	Good	[n/r]	[n/r]
	Ethyl Cyclopentane	Best	[n/r]	[n/r]	[n/r]
Wash	Ethylene Chloride	Do Not Use	Do Not Use	Do Not Use	Best
	Ethylene Chlorohydrin	Do Not Use	Best	Best	Do Not Use
	Ethylene Diamine	Best	Best	[n/r]	Do Not Use
Test	Ethylene Dibromide	[n/r]	[n/r]	[n/r]	Best
	Ethylene Dichloride	Do Not Use	Do Not Use	Do Not Use	Best
	Ethylene Glycol	Best	Best	Best	Best
	Ethylene Oxide, Liquid	Do Not Use	Best	Best	Best
	Ethylmorpholine Stannous	[n/r]	Best	[n/r]	[n/r]
E					
	Fatty Acids	Best	Do Not Use	Good	Best
	Fenamiphos	[n/r]	[n/r]	[n/r]	Best
	Ferric Chloride	Best	Best	Best	Best
	Ferric Nitrate	Best	Best	[n/r]	Best
	FLUOMETURON FLOWABLE	Best	[n/r]	[n/r]	[n/r]
	Fluorolube	Good	Best	[n/r]	Good
	FOLICUR 250 EC	[n/r]	Best	[n/r]	[n/r]
	FOLICUR 250 EW	Best	[n/r]	[n/r]	[n/r]

		GT 100	GT 200	GT 200S	GT 300
E		NITRILE	EPDM	Santoprene	VITON
	FOLICUR 430 SC	Best	[n/r]	[n/r]	[n/r]
	FOLIDOL M500	[n/r]	[n/r]	[n/r]	Best
	FOLIMAT 800	[n/r]	Best	[n/r]	[n/r]
	Formaldehyde	Caution	Good	Best	Best
	Formalin	Caution	Good	[n/r]	[n/r]
	FUEL DOCTOR	[n/r]	[n/r]	[n/r]	Best
	Fuel Oil	Best	Do Not Use	[n/r]	Best
	Formic Acid	Do Not Use	n/r	Best	Best
	Furfural Alcohol	Do Not Use	Caution	[n/r]	Best
	Fumaric Acid	Good	[n/r]	[n/r]	Best
Test	Furfural	Do Not Use	Best	[n/r]	Good
	Furfuraldehyde	[n/r]	Best	[n/r]	[n/r]
	Furylcarbinol	[n/r]	Best	[n/r]	[n/r]
G					
	Gallic Acid	Best	Best	[n/r]	Best
	Gasoline Leaded	Good	Caution	Do Not Use	Best
	Gelatin	Best	Best	[n/r]	Best
Wash	Glacial Acetic Acid	Do Not Use	Do Not Use	[n/r]	Good
	Glaubers Salt	[n/r]	[n/r]	[n/r]	Best
	Glucose	Best	Best	Best	Best
	Gluearaldehyde	do not use	best	do not use	do not use
	Glycerin	Best	Best	Best	Best
	Glycols	Best	Best	Best	Best
	Green Sulfate Liquor	Best	Best	[n/r]	Best
	GUSATHION 200 SC	Best	[n/r]	[n/r]	[n/r]
	GUSATHION A LIQUID	[n/r]	[n/r]	[n/r]	Best
H					
	Halothane	[n/r]	[n/r]	[n/r]	Best
	Halowax Oil	Caution	Caution	[n/r]	Best
	Heavy Water	Best	[n/r]	[n/r]	[n/r]
	HELOTHION EC	[n/r]	[n/r]	[n/r]	Best
	Hexyl Alcohol	Best	Good	[n/r]	Best
Test	HFE Fluids [3M/Novoc]	[n/r]	Best	[n/r]	Best
	Hydraulic Fluid	best	good	good	do not use
Test	Hydraulic Oils (Petroleum)	Best	Do Not Use	[n/r]	Best
	Hydrazine	Best	Best	Best	Best
	Hydrobromic Acid	Do Not Use	Best	Best	Best
	Hydrochloric Acid (5-20%)	Caution	Best	Best	Caution
	Hydrochloric Acid (25-30%)	Caution	Good	Best	Best
	Hydrochloric Acid (35%)	Do Not Use	Caution	Best	Best
	Hydrocyanic Acid	Good	Good	Best	Good
	Hydrofluosilicic Acid	Do Not Use	Good	[n/r]	Best
	Hydrogen Peroxide 35%	Do Not Use	Do Not Use	Best	Best
	Hydrogen Peroxide 90%	Do Not Use	Do Not Use	Do Not Use	Best
	Hydrogen Sulfide (Wet) (Cold)	Good	Best	Best	Best
	Hydrogen Sulfide (Wet) (Hot)	Caution	Best	[n/r]	Good
Wash	Hydroquinone	Best	Best	[n/r]	Best
	Hypochlorous Acid 10%	Caution	Good	[n/r]	Good
I					
	Iodine (in Alcohol)	Good	Caution	[n/r]	Best
	Isocetane	Best	Do Not Use	Do Not Use	Best
	Isobutyl Alcohol	Good	Best	[n/r]	Best
	Isobutyl-n-Butyrate	[n/r]	Best	[n/r]	[n/r]
	Isododecane	Best	[n/r]	[n/r]	[n/r]
	Isopropanol	Best	Best	Best	Best
Wash	Isopropyl Acetate	Do Not Use	Good	[n/r]	Do Not Use
	Isopropyl Alcohol	Best	Best	Best	Best
Wash	Isopropyl Amine	[n/r]	Good	[n/r]	[n/r]

All trademarks and registered trademarks are property of their respective corporations.

GoatThroat™ Chemical Compatibility Guide

		GT 100	GT 200	GT 200S	GT 300
		NITRILE	EPDM	Santoprene	VITON
	J				
	Isopropyl Chloride	Good	Do Not Use	[n/r]	Best
Wash	Isopropyl Ether	Best	Caution	Good	Caution
	Isopropyl myristate 98%	[n/r]	[n/r]	Good	[n/r]
	Isothiazol	do not use	do not use	do not use	best
	K				
	KELTHANE	[n/r]	[n/r]	[n/r]	Best
Test	Kerosene	Best	Do Not Use	Do Not Use	Best
	KILVAL	[n/r]	[n/r]	[n/r]	Best
	Kordek 50C	do not use	do not use	do not use	best
	L				
	Lactams- Amino Acids	[n/r]	Best	[n/r]	[n/r]
	Lactic Acid	Best	Best	Best	Best
Wash	Lactones	[n/r]	Good	[n/r]	[n/r]
	Lard	Best	Good	[n/r]	Best
	LARVIN LV	[n/r]	[n/r]	[n/r]	Best
	Lavender Oil	Good	Do Not Use	[n/r]	Best
	LARVIN 375	Best	[n/r]	[n/r]	[n/r]
	LE - MAT	[n/r]	Best	[n/r]	[n/r]
	Lead Acetate	Best	Best	Best	Best
	Lead Nitrate	Best	Best	[n/r]	Best
	Lead Sulfamate	Good	Best	[n/r]	Best
	LEAFEX	Best	[n/r]	[n/r]	Best
	LEBAYCID	[n/r]	[n/r]	[n/r]	Best
	LEGUMEX	Best	[n/r]	[n/r]	[n/r]
	Light Grease	Best	[n/r]	[n/r]	[n/r]
	Lime Bleach	Best	Best	[n/r]	Best
	Lime Sulphur	Do Not Use	Best	[n/r]	Best
	Linoleic Acid	Good	Do Not Use	[n/r]	Best
	Linseed Oil	Good	Good	Good	Best
	Lubricating Oils (Petroleum)	Best	Do Not Use	Good	Best
	Lye	Good	Good	[n/r]	Good
	M				
	Macro-Sorb	do not use	do not use	do not use	best
	MALDISON 500	[n/r]	[n/r]	[n/r]	Best
	Magnesium Chloride	Best	Best	Best	Best
	Magnesium Hydroxide	Best	Best	Best	Best
	Magnesium Salts	Best	Best	Best	Best
	Magnesium Sulfate	Best	Best	Best	Best
	Magnesium Sulphite	Best	[n/r]	[n/r]	[n/r]
	MALATHION	Best	[n/r]	[n/r]	[n/r]
	Maleic Acid	Good	Best	[n/r]	Best
	Maleic Anhydride	Do Not Use	Do Not Use	[n/r]	Best
	Malic Acid	Best	Best	[n/r]	Best
	MARLIN	[n/r]	[n/r]	[n/r]	Best
	MCPA	Best	Best	[n/r]	Best
	MCPA 375 SALT	Best	Best	[n/r]	Best
	MCPA LVE 500	Best	Best	[n/r]	Best
	Mercuric Chloride (Dilute Solu)	Best	Best	Best	Best
Wash	Mesityl Oxide	Do Not Use	Good	[n/r]	Do Not Use
Wash	METASYSTOX	[n/r]	[n/r]	[n/r]	Best
Wash	Methacrylic Acid	[n/r]	Caution	[n/r]	Good
	Methalated Spirits	[n/r]	Best	[n/r]	[n/r]
	Methamidol	[n/r]	Best	[n/r]	[n/r]
	Methane	Best	Best	[n/r]	Best

		GT 100	GT 200	GT 200S	GT 300
		NITRILE	EPDM	Santoprene	VITON
	M				
	Methanol	Good	Best	[n/r]	Good
Wash	Methyl Acetate	Do Not Use	Good	[n/r]	Do Not Use
	Methyl Acrylate	Do Not Use	Good	[n/r]	Do Not Use
	Methyl Alcohol	Good	Good	Good	Best
Test	Methyl Bromide	Do Not Use	Good	Good	Best
	Methyl Butyl Ketone	Do Not Use	Best	Best	Do Not Use
	Methyl Cellosolve	Good	Do Not Use	[n/r]	Good
Wash	Methyl Cellulose	Do Not Use	Good	[n/r]	Do Not Use
Test	Methyl Chloride	Do Not Use	Good	Do Not Use	Do Not Use
	Methyl Chloroformate	[n/r]	[n/r]	[n/r]	Best
	Methyl D-Bromide	[n/r]	[n/r]	[n/r]	Best
	Methyl Ether	Good	Do Not Use	[n/r]	Do Not Use
	Methyl Ethyl Ketone (MEK)	Do Not Use	Good	Good	Do Not Use
	Methyl Isopropyl Ketone	Do Not Use	Do Not Use	[n/r]	Do Not Use
	Methyl Mercaptan	[n/r]	Best	[n/r]	[n/r]
	Methyl Oleate	Do Not Use	Caution	[n/r]	Best
	Methyl Salicylate	Caution	Caution	Best	Good
Wash	Methylacrylic Acid	[n/r]	Good	[n/r]	Good
	Methylcyclopentane	Do Not Use	Do Not Use	[n/r]	Best
Test	Methylene Chloride	Do Not Use	Do Not Use	Do Not Use	Caution
Test	Methyl Dichloride	Do Not Use	Do Not Use	[n/r]	Good
	Milk	Best	Best	Best	Best
	Millenium Clean	do not use	do not use	best	do not use
	Mineral Oil	Best	Do Not Use	Good	Best
	Momentum	do not use	do not use	do not use	best
Test	Monobromobenzene	[n/r]	[n/r]	[n/r]	Best
Test	Monochlorobenzene	Do Not Use	Do Not Use	[n/r]	Best
Test	Monoethanolamine	Best	Best	[n/r]	Do Not Use
	Monoethylene	[n/r]	Best	[n/r]	[n/r]
	Monomethyl Aniline	Do Not Use	Do Not Use	[n/r]	Best
	Monovinyl Acetylene	Best	Best	[n/r]	Best
	N				
	Naptha	Caution	Do Not Use	Do Not Use	Best
	Napthalene	Do Not Use	Do Not Use	Good	Best
	Napthenic Acid	Good	Do Not Use	[n/r]	Best
Wash	N-Butyl Acetate	[n/r]	Good	[n/r]	[n/r]
	N-Butyl Benzoate	[n/r]	Best	[n/r]	[n/r]
	N-Butyl Butyrate	[n/r]	Best	[n/r]	[n/r]
	Neatsfoot Oil	Best	Caution	[n/r]	Best
	NEMACUR 400 EC	[n/r]	[n/r]	[n/r]	Best
	Neon	Best	[n/r]	[n/r]	[n/r]
	Neville Acid	Caution	Caution	[n/r]	Best
	Nickel Acetate	Best	Best	[n/r]	Caution
	Nickel Chloride	Best	Best	[n/r]	Best
	Nickel Sulfate	Best	Best	Best	Best
	NITOFOL	[n/r]	Best	[n/r]	[n/r]
	Nitric Acid 5-10% Solution	Do Not Use	Best	Best	Best
	Nitric Acid 20-50% Solution	Do Not Use	Do Not Use	Best	Best
	Nitric Acid 60-70% Solution	Do Not Use	Do Not Use	Do Not Use	Best
	Nitric Acid 70%+ Solution	Caution	Do Not Use	Do Not Use	Do Not Use
	Nitrobenzene	Do Not Use	Good	Best	Best
	Nitromethane	Do Not Use	Good	[n/r]	Do Not Use
	N-Methyl-2pyrrolidone	do not use	best	best	do not use
	N-Octane	Best	Caution	[n/r]	Best
	No-Mow	do not use	do not use	do not use	best
	Novac HFE 71DE	do not use	do not use	do not use	best
	Novac HFE 72DE	do not use	do not use	do not use	best
	N-Pentane	Best	[n/r]	[n/r]	Best
	N-Propyl Acetone	[n/r]	Best	[n/r]	[n/r]

All trademarks and registered trademarks are property of their respective corporations.

GoatThroat™ Chemical Compatibility Guide

		GT 100	GT 200	GT 200S	GT 300
O		NITRILE	EPDM	Santoprene	VITON
	O-Chlorophenol	[n/r]	[n/r]	[n/r]	Best
Test	Octachlorotoluene	Caution	Caution	[n/r]	Best
	Octadecane	Best	Caution	[n/r]	Best
	Octagon PD 680	best	do not use	do not use	best
	Octyl-Alcohol	Best	[n/r]	[n/r]	[n/r]
Test	O-Dichlorobenzene	Best	Caution	[n/r]	Best
	OFTANOL TURF	[n/r]	[n/r]	[n/r]	Best
	Oleic Acid	Do Not Use	Do Not Use	Best	Best
	Olive Oil	Best	Good	[n/r]	Best
	OMALA OIL 220	Best	[n/r]	[n/r]	[n/r]
	Orthochloro Ethyl Benzene	[n/r]	[n/r]	[n/r]	Best
	Oxalic Acid (Cold)	Best	Best	Best	Best
	OXAMIN LO	Best	[n/r]	[n/r]	[n/r]

		GT 100	GT 200	GT 200S	GT 300
P		NITRILE	EPDM	Santoprene	VITON
	Palmitic Acid	Best	Good	Best	Best
	PANOCTINE	Best	[n/r]	[n/r]	[n/r]
	Pantendiol	do not use	best	do not use	do not use
	Paraffin Oil	Best	[n/r]	[n/r]	Best
	Parathion Ethyl Methyl	[n/r]	[n/r]	[n/r]	Best
	P-Cymene	[n/r]	[n/r]	[n/r]	Best
	P-Dichlorobenzene	[n/r]	[n/r]	[n/r]	Best
	Peanut Oil	Best	Do Not Use	[n/r]	Best
	Penair Mil-C-85590	do not use	do not use	do not use	best
	Pentane 2 Methyl	Best	[n/r]	[n/r]	[n/r]
	Pentane 2-4 Dimethyl	Best	[n/r]	[n/r]	[n/r]
	Pentane 3 Methyl	Best	[n/r]	[n/r]	[n/r]
Test	Perchloric Acid 72%	Do Not Use	Good	Do Not Use	Best
	Perchloroethylene	Do Not Use	Do Not Use	Do Not Use	Best
	Petroleum	Best	Best	Do Not Use	Best
	Phenol (Carbolic Acid)	Caution	Do Not Use	Good	Best
	Phenylbenzene	Do Not Use	Caution	[n/r]	Best
Test	Phenyl Hydrazine	Do Not Use	Good		Do Not Use
	Phorone	Caution	Caution	[n/r]	Best
	Phosphoric Acid (to 40% Solution)	Do Not Use	Good	Best	Best
	Phosphoric Acid 40-100% Solution	Do Not Use	Good	Caution	Best
	Phosphoric Acid Crude	Caution	Good	[n/r]	Best
	Phosphoric Acid-20%	Caution	Good	Best	Best
	Phosphoric Acid-45%	Best	Best	Best	Best
Test	Phosphorous Trichloride Acid	Caution	Best	Best	Best
	Pickling Solution	[n/r]	Do Not Use	Best	Good
	Picric Acid	Do Not Use	Good	[n/r]	Best
	Pine Oil	Best	[n/r]	[n/r]	[n/r]
	Pinene	Do Not Use	Good	[n/r]	Best
	Plating Solutions: Antimony	Best	[n/r]	[n/r]	Best
	Plating Solutions: Arsenic	Best	[n/r]	[n/r]	Best
	Plating Solutions: Brass	Best	[n/r]	[n/r]	Best
	Plating Solutions: Bronze	Best	[n/r]	[n/r]	Best
	Plating Solutions: Cadmium	Best	[n/r]	[n/r]	Best
	Plating Solutions: Chrome	Caution	Best	[n/r]	Best
	Plating Solutions: Copper	Best	[n/r]	[n/r]	Best
	Plating Solutions: Gold	Best	[n/r]	[n/r]	Best
	Plating Solutions: Indium	Best	[n/r]	[n/r]	Best
	Plating Solutions: Iron	Best	[n/r]	[n/r]	Best
	Plating Solutions: Lead	Best	[n/r]	[n/r]	Best
	Plating Solutions: Nickel	Best	[n/r]	[n/r]	Best
	Plating Solutions: Silver	Best	[n/r]	[n/r]	Best
	Plating Solutions: Tin	Best	[n/r]	[n/r]	Best
	Plating Solutions: Zinc	Best	[n/r]	[n/r]	Best
	Polyvinyl Acetate Emulsion	Best	Best	[n/r]	Best

		GT 100	GT 200	GT 200S	GT 300
P		NITRILE	EPDM	Santoprene	VITON
	Potassium Acetate	Best	Best	[n/r]	Best
	Potassium Borate	Best	nr	Best	Best
	Potassium Bromate	Best	nr	Best	Best
	Potassium Bromide	Best	nr	Best	Best
	Potassium Chloride	Best	Best	Best	Best
	Potassium Cupro Cyanide	Best	Best	[n/r]	Best
	Potassium Cyanide Solutions	Best	Best	Best	Best
	Potassium Dichromate	Best	Best	Best	Best
Test	Potassium Hydroxide 60%	Do Not Use	Best	Best	Do Not Use
	Potassium Nitrate	Best	Best	[n/r]	Best
	Potassium Salts	Best	[n/r]	[n/r]	[n/r]
	Potassium Sulfate	Best	Best	Best	Best
Wash	PREP 720	Good	[n/r]	[n/r]	[n/r]
	PRIMAL ASE-60	Best	[n/r]	[n/r]	[n/r]
	Propane (Liquified) (LPG)	Best	Caution	Do Not Use	Best
Wash	Propyl Acetate	Do Not Use	Good	[n/r]	Do Not Use
	Propyl Alcohol	Good	Best	[n/r]	Best
	Propyl Nitrate	[n/r]	Good	[n/r]	Do Not Use
	Propylene	Do Not Use	Do Not Use	[n/r]	Best
	Propylene Glycol	Best	Best	Best	Best
	Prothiofos	[n/r]	[n/r]	[n/r]	Best
	Proxel GL	do not use	do not use	do not use	best
	P-Tertiary Butyl Catechol	[n/r]	Best	[n/r]	[n/r]
	Pyridine Oil	Do Not Use	Good	[n/r]	Do Not Use
Wash	Pyroigneous Acid	Good	Caution	[n/r]	Best
	Pyrolubo	[n/r]	[n/r]	[n/r]	Best
Q		NITRILE	EPDM	Santoprene	VITON
	QUINTOZENE FLOWABLE	Best	[n/r]	[n/r]	[n/r]
R		NITRILE	EPDM	Santoprene	VITON
	Rapeseed Oil	Do Not Use	Best	[n/r]	Best
	RAXIL C Flowable seed dressing	Best	[n/r]	[n/r]	[n/r]
	ROGOR 400	[n/r]	[n/r]	[n/r]	Best
	Roots 1-2-3	do not use	best	n/r	best
	ROVRAL AQUAFLO	Best	[n/r]	[n/r]	[n/r]
	ROVRAL LIQUID	Best	[n/r]	[n/r]	[n/r]
	ROVRAL LIQUID S.D.	Best	[n/r]	[n/r]	[n/r]
	ROUNDUP	n/r	n/r	n/r	BEST
S		NITRILE	EPDM	Santoprene	VITON
	Sal Ammoniac	Best	Best	[n/r]	Best
	Salicylic Acid	Best	Best	[n/r]	Best
	SANTICIZER	[n/r]	Best	[n/r]	[n/r]
	Sea Water	Best	Best	Best	Best
	SEMEVIN 500 P	Best	[n/r]	[n/r]	[n/r]
	SENCOR 480 SC	Best	[n/r]	[n/r]	[n/r]
	Silicate Esters	Good	Do Not Use	[n/r]	Best
	Silicone Greases	Best	Best	Best	Best
	Silicone Oils	Best	Best	Do Not Use	Best
	Silicone Fluid	[n/r]	[n/r]	Good	[n/r]
	Silver Nitrate	Best	Best	Best	Best
	Soap Solutions	Best	Best	Best	Best
	Soda Ash (Sodium Carbonate)	Best	Best	[n/r]	Best
	Sodium Acetate	Best	Best	[n/r]	Good
	Sodium Bicarbonate (Baking Soda)	Best	Best	Best	Best
	Sodium Bisulfate	Best	Best	Best	Best
	Sodium Bisulfite	Best	Best	Best	Best
	Sodium Borate	Best	Best	Best	Best
	Sodium Carbonate	Good	Best	Best	Best
	Sodium Chloride (Salt)	Best	Best	Best	Best

All trademarks and registered trademarks are property of their respective corporations.

GoatThroat™ Chemical Compatibility Guide

	S	GT 100	GT 200	GT 200S	GT 300
		NITRILE	EPDM	Santoprene	VITON
	Sodium Cyanide	Best	Best	[n/r]	Best
	Sodium Hydroxide (20% Solution)	Best	Best	Best	Good
	Sodium Hydroxide (50% Solution)	Best	Best	Best	Do Not Use
	Sodium Hydroxide (80% Solution)	Do Not Use	Best	[n/r]	Do Not Use
	Sodium Hypochlorite (to 5%)	Good	Good	Best	Best
	Sodium Hypochlorite (to 15%)	Do Not Use	Best	Best	Best
	Sodium Lauryl Sulfate (dodecyl sulfate 70%)	[n/r]	[n/r]	Best	[n/r]
Test	Sodium Metaphosphate	Best	Best	[n/r]	Best
	Sodium Nitrate	Best	Best	Best	Best
	Sodium Perborate	Good	Best	[n/r]	Best
	Sodium Peroxide	Best	Best	[n/r]	Best
	Sodium Phosphate	Best	Best	Best	Best
	Sodium Phosphate, Monobasic	Best	Best	[n/r]	Best
	Sodium Phosphate, Tribasic	Best	Best	[n/r]	Best
	Sodium Salts	Best	[n/r]	[n/r]	[n/r]
	Sodium Silicate	Best	Best	[n/r]	Best
	Sodium Sulphate	Best	Best	Best	Best
	Sodium Sulfide	Best	Best	Best	Best
	Sodium Sulphite	Best	Best	[n/r]	Best
	Sodium Thiosulphate (Hypo)	Best	Best	[n/r]	Best
	Sorbitan Monolaurate Polyoxethylene	Best	[n/r]	[n/r]	[n/r]
	Soybean Oil	Best	Best	Good	Best
	SPIN FLOWABLE	Best	[n/r]	[n/r]	[n/r]
	Stannic Chloride	Best	Best	[n/r]	Best
	Stannous Chloride	Best	Good	Best	Best
	Stearic Acid	Good	Do Not Use	Best	Best
	Sucrose Solution	Best	Best	[n/r]	Best
	Sulfurous Acid	Caution	Best	[n/r]	Best
	Sulfur Chloride	Caution	Do Not Use	[n/r]	Best
	Sulphur Hexafluoride	Good	Best	[n/r]	Best
	Sulphur Liquors	[n/r]	[n/r]	[n/r]	Best
	Sulfuric Acid (10-30%)	Best	Best	Best	Best
	Sulfuric Acid (35-80%)	Good	Do Not Use	Do Not Use	Best
	Sulfuric Acid (85-90%)	Caution	Do Not Use	Do Not Use	Best
	Sulfuric Acid (90%+)	Do Not Use	Do Not Use	Do Not Use	Best
	SUPRACIDE	[n/r]	[n/r]	[n/r]	Best
	I				
	Tannic Acid	Best	Good	Best	Best
	Tartaric Acid	Best	Best	Best	Best
	Tergitol	[n/r]	[n/r]	Good	[n/r]
	TERIC GN9	Best	[n/r]	[n/r]	[n/r]
	Terpineol	Good	Caution	[n/r]	Best
	Tertiary Butyl Alcohol	Do Not Use	Good	[n/r]	Best
Test	Tera Bromoethane	Do Not Use	Best	[n/r]	Best
	Tetrabutyl Titanate	Good	Good	[n/r]	Best
Test	Tetrachloroethylene	Do Not Use	Do Not Use	Do Not Use	Best
Test	Tetrachloroethane	Do Not Use	Do Not Use	Do Not Use	Best
	Tetraethyl Lead	Good	Caution	[n/r]	Best
Wash	Tetrahydrofuran	Do Not Use	Do Not Use	Good	Do Not Use
Test	Tetraline	Caution	Do Not Use	[n/r]	Best
Test	Thinners	Caution	Caution	Best	Caution
Test	Titanium Tetrachloride	Caution	Do Not Use	[n/r]	Best
	TOKUTHION	[n/r]	[n/r]	[n/r]	Best
Test	Toluene	Do Not Use	Good	Do Not Use	Best
Wash	Toluene Diisocyanate	[n/r]	Best	[n/r]	[n/r]
	TOTRIL	[n/r]	[n/r]	[n/r]	Best

	I	GT 100	GT 200	GT 200S	GT 300
		NITRILE	EPDM	Santoprene	VITON
	TOUGH 450 EC	[n/r]	Best	[n/r]	[n/r]
	Transformer Oil	Best	Do Not Use	[n/r]	Do Not Use
	Transmission Fluid Type A	Best	Caution	[n/r]	Best
	Triacetin	Good	Best	[n/r]	Good
	Triaryl Phosphate	[n/r]	Best	[n/r]	[n/r]
	Tributoxy Ethyl Phosphate	Caution	Best	[n/r]	Good
	Tributyl Phosphate	Do Not Use	Good	[n/r]	Do Not Use
	Tributyl Trichloroacetic Acid	[n/r]	Caution	[n/r]	[n/r]
	Trichloroethylene	Do Not Use	Do Not Use	Do Not Use	Best
	Tricresylphosphate	Caution	Best	[n/r]	Good
	TRIDAN	[n/r]	[n/r]	[n/r]	Best
	Triethanol Amine	Caution	Best	Best	Do Not Use
Wash	Tri-isopropanolamine	[n/r]	Good	[n/r]	[n/r]
Wash	Trinitrol Toluene	Do Not Use	Do Not Use	[n/r]	Good
	Trioctyl Phosphate	Do Not Use	Best	[n/r]	Do Not Use
	Tripoly Phosphate	[n/r]	Best	[n/r]	[n/r]
	TruBlue Deoderizer	do not use	best	best	best
	Tung Oil	Best	Do Not Use	Good	Best
	Turbine Oil	Best	Do Not Use	[n/r]	Best
	Turbo Oil	Best	[n/r]	[n/r]	[n/r]
Test	Turpentine	Good	Good	[n/r]	Best
	TWEEN 20	Best	[n/r]	[n/r]	[n/r]
	U				
	Urea	Best	n/r	Best	Best

	V	GT 100	GT 200	GT 200S	GT 300
		NITRILE	EPDM	Santoprene	VITON
	Varnish	Best	Do Not Use	[n/r]	Best
	Vaporene	do not use	best	do not use	do not use
	Vegetable Oils	Best	Best	[n/r]	Best
Test	Vertrel Solvents (Dupont)	[n/r]	Best	[n/r]	[n/r]
	Vinegar	Caution	Best	Best	Best
	W				
	Water	Best	Best	Best	Best
	White Oil	Best	Caution	[n/r]	Best
	White Pine Oil	Good	Caution	[n/r]	Best
	Wine and Whiskey	Best	Best	Best	Best
	Wood Oil	Best	Good	[n/r]	Best
	X				
	X77	Best	[n/r]	[n/r]	[n/r]
	Xenon	Best	[n/r]	[n/r]	[n/r]
	Xylene	Caution	Do Not Use	Do Not Use	Good
	Xylol	do not use	do not use	do not use	Good
	Z				
	Zeolites	Good	Best	[n/r]	Best
	Zinc Acetate	Best	Best	[n/r]	Best
	Zinc Chloride	Best	Best	Best	Best
	Zinc Salts	Best	[n/r]	Best	[n/r]
	Zinc Sulfate	Best	Best	Best	Best

All trademarks and registered trademarks are property of their respective corporations.